

巴氏、布氏、维氏、韦氏、洛氏硬度值换算表

深圳市恒信杰科技有限公司

地址：深圳市宝安新中心区华美居商务楼A区5楼555室

电话：0755-29764395 29764385

传真：0755-29764385

<http://www.hengxinjie.com> www.sz-hxkj.cn www.sz-hengxin.cn www.hxj17.com

巴氏 GYZJ 934-1	布氏 10mm 500kg	维氏 5kg	韦氏 B	洛氏				巴氏 GYZJ 934-1	布氏 10mm 500kg	维氏 5kg	韦氏 B	洛氏			
				B	E	F	H					B	E	F	H
35		21					32	68	60	65	11.0		71	70	94
36		22					35	69	62	67	11.4		73	72	95
37		23					37	70	64	70	11.8	17	75	74	97
38		24					40	71	67	72	12.2	23	76	75	98
39		25					42	72	69	75	12.6	28	78	77	99
40	25	26					45	73	72	78	12.9	33	80	79	100
41	25	27					47	74	75	81	13.3	38	81	80	101
42	26	28					49	75	78	85	13.7	42	83	82	102
43	27	29					51	76	80	88	14.0	47	84	83	103
44	27	30					54	77	84	92	14.3	51	86	85	104
45	28	30					56	78	87	95	14.7	55	87	86	105
46	29	31					58	79	90	99	15.0	59	89	88	106
47	30	32			23		60	80	94	103	15.3	63	90	89	106
48	30	33	0.7		26		62	81	97	108	15.6	66	91	90	107
49	31	34	1.3		28		64	82	101	112	15.9	70	92	91	108
50	32	35	1.9		31		66	83	105	117	16.2	73	94	92	109
51	33	36	2.5		34		68	84	109	121	16.4	76	95	93	109
52	34	38	3.1		36		70	85	113	126	16.7	79	96	94	110
53	35	39	3.6		39	30	72	86	117	131	16.9	81	97	95	111
54	37	40	4.2		41	34	73	87	121	137	17.2	84	98	96	111
55	38	41	4.7		44	37	75	88	126	142	17.4	86	99	97	112
56	39	43	5.3		46	40	77	89	130		17.6	88	100	98	112
57	40	44	5.8		48	43	78	90	135		17.8	90	101	98	113
58	42	45	6.3		50	46	80	91	140		18.0		102	99	114
59	43	47	6.8		53	48	82	92	145		18.2		103	100	
60	45	49	7.3		55	51	83	93			18.4		103	100	
61	46	50	7.8		57	54	85	94			18.6		104	101	
62	48	52	8.3		59	56	86	95			18.7		105	102	
63	50	54	8.8		61	59	88	96			18.9		106	102	
64	51	56	9.2		63	61	89	97			19.0		106	103	
65	53	58	9.7		65	63	90	98			19.2		107		
66	55	60	10.1		67	66	92	99			19.3		107		
67	57	62	10.6		69	68	93	100			19.4		108		

[注]本硬度换算表来源：美国巴勃·考曼(Baber Colman)公司巴氏硬度计使用说明书